


ENN_12_SV_14_CRUSH_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_12_SV_14_CRUSH_5K\ENN_12_SV_14_CRUSH_5K043.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_12_SV_14_CRUSH_5K.afg
 Time: 5/15/2015, 13:51, duration 17 min 28 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 25459184, CCD-Z = 274250
 Velocity adaption: no
 Fitting: no

Material:

| ASTM(+) | No(-) | retained [%] | passing [%] | SPHT3 | Symm3 | b/l3 | PDN |
|---------|-------|--------------|-------------|-------|-------|-------|----------|
| > #16 | | 0.0 | 100.0 | | | | 0 |
| #20 | #16 | 0.0 | 100.0 | | | | 0 |
| #30 | #20 | 0.0 | 100.0 | | | | 0 |
| #40 | #30 | 0.4 | 100.0 | 0.856 | 0.877 | 0.788 | 432 |
| #50 | #40 | 12.8 | 99.6 | 0.901 | 0.896 | 0.782 | 35965 |
| #60 | #50 | 28.5 | 86.8 | 0.922 | 0.908 | 0.774 | 146827 |
| #70 | #60 | 26.8 | 58.3 | 0.922 | 0.911 | 0.749 | 203799 |
| #140 | #70 | 26.4 | 31.5 | 0.905 | 0.905 | 0.722 | 596323 |
| PAN | #140 | 5.1 | 5.1 | 0.846 | 0.900 | 0.677 | 39314381 |



Mean value SPHT3 = 0.906
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.737
 Mean value RDNS_C3 = 0.608
 Mean value SPHT_K3 = 0.680

User