


ENN_12_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_12_SV_14_CRUSH_6K\ENN_12_SV_14_CRUSH_6K042.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_12_SV_14_CRUSH_6K.afg
 Time: 5/15/2015, 12:44, duration 20 min 57 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 69524209, CCD-Z = 878938
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.935	0.917	0.770	1
#40	#30	0.3	100.0	0.854	0.876	0.788	627
#50	#40	11.4	99.7	0.906	0.899	0.786	61876
#60	#50	27.5	88.3	0.923	0.909	0.776	270874
#70	#60	26.2	60.8	0.923	0.911	0.752	382050
#140	#70	27.8	34.6	0.908	0.906	0.726	1230193
PAN	#140	6.8	6.8	0.864	0.905	0.696	98893939



Characteristics

Q3 [%]	x [μm]
10.0	126.2
50.0	235.8
90.0	305.9
SPAN3 =	0.762
U3 =	1.972
Mv3(x) =	226.4 μm
Sigma3(x) =	71.8 μm

Mean value SPHT3 = 0.908
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.739
 Mean value RDNS_C3 = 0.620
 Mean value SPHT_K3 = 0.683

User