


ENN_13_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_13_SV_14_PRECRUSH\ENN_13_SV_14_PRECRUSH080.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_13_SV_14_PRECRUSH.afg
 Time: 5/20/2015, 15:57, duration 10 min 28 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 5095006, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		18.8	100.0	0.745	0.874	0.698	968
#20	#16	20.1	81.2	0.751	0.876	0.665	2721
#30	#20	17.4	61.1	0.763	0.875	0.664	6206
#40	#30	10.7	43.7	0.781	0.872	0.668	10981
#50	#40	7.7	33.0	0.813	0.872	0.684	23313
#60	#50	3.5	25.3	0.842	0.875	0.699	24302
#70	#60	3.5	21.8	0.868	0.882	0.714	41079
#140	#70	15.4	18.3	0.906	0.894	0.726	719481
PAN	#140	2.9	2.9	0.933	0.897	0.716	4265955



Characteristics

Q3 [%]	x [μm]
10.0	152.2
50.0	696.1
90.0	1369.0
SPAN3 =	1.748
U3 =	5.483
Mv3(x) =	725.4 μm
Sigma3(x) =	460.8 μm

Mean value SPHT3 = 0.786
 Mean value Symm3 = 0.877
 Mean value b/l3 = 0.668
 Mean value RDNS_C3 = 0.244
 Mean value SPHT_K3 = 0.539

User