


ENN_14_SV_14_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_14_SV_14_CRUSH5K\ENN_14_SV_14_CRUSH5K135.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_14_SV_14_CRUSH5K.afg
 Time: 6/15/2015, 11:05, duration 26 min 5 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 52625657, CCD-Z = 830139
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.686	0.748	0.720	195
#60	#50	1.2	100.0	0.870	0.869	0.772	9354
#70	#60	11.8	98.8	0.914	0.899	0.774	142432
#140	#70	78.2	87.0	0.915	0.908	0.744	2696573
PAN	#140	8.8	8.8	0.883	0.914	0.719	91035008



Characteristics

Q3 [%]	x [μm]
10.0	110.7
50.0	169.3
90.0	217.4
SPAN3 =	0.630
U3 =	1.621
Mv3(x) =	164.8 μm
Sigma3(x) =	45.0 μm

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.731
 Mean value RDNS_C3 = 0.635
 Mean value SPHT_K3 = 0.663

User