


ENN_14_SV_14_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_14_SV_14_CRUSH6K\ENN_14_SV_14_CRUSH6K133.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_14_SV_14_CRUSH6K.afg
 Time: 6/15/2015, 10:01, duration 26 min 25 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 101687962, CCD-Z = 902675
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.897	0.922	0.708	1
#40	#30	0.0	100.0	0.859	0.903	0.702	2
#50	#40	0.1	100.0	0.714	0.778	0.726	417
#60	#50	1.2	99.9	0.858	0.863	0.766	12179
#70	#60	10.9	98.7	0.909	0.896	0.773	172584
#140	#70	75.3	87.8	0.910	0.905	0.743	3412412
PAN	#140	12.5	12.5	0.857	0.900	0.696	203247965



Characteristics

Q3 [%]	x [μm]
10.0	92.1
50.0	166.0
90.0	216.2
SPAN3 =	0.748
U3 =	1.917
Mv3(x) =	159.5 μm
Sigma3(x) =	50.1 μm

Mean value SPHT3 = 0.896
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.568
 Mean value SPHT_K3 = 0.654

User