


ENN_14_SV_14_SHERE_AND_ROUND

Company:	
User:	
Result file:	C:\...CAMDAT\ENN_14_SV_14_SHERE_AND_ROUND\ENN_14_SV_14_SHERE_AND_ROUND121.rdf
Task file:	C:\CamsizerXT\CAMSYS\ENN_14_SV_14_SHERE_AND_ROUND.afg
Time:	6/12/2015 , 11:00 , duration 8 min 28 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 891890 , CCD-Z = 26158
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.2	100.0	0.664	0.726	0.716	68
#60	#50	2.3	99.8	0.846	0.852	0.750	1840
#70	#60	17.1	97.5	0.897	0.890	0.753	21232
#140	#70	79.2	80.4	0.901	0.901	0.721	248757
PAN	#140	1.2	1.2	0.838	0.906	0.620	5880188



Mean value SPHT3 = 0.890
Mean value Symm3 = 0.895
Mean value b/l3 = 0.711
Mean value RDNS_C3 = 0.553
Mean value SPHT_K3 = 0.619

User