


ENN_15_REDO_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_15_REDO_CRUSH5K\ENN_15_REDO_CRUSH5K117.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_15_REDO_CRUSH5K.afg
 Time: 6/11/2015, 15:02, duration 28 min 56 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 50636679, CCD-Z = 492094
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.883	0.893	0.700	8
#50	#40	0.1	100.0	0.697	0.765	0.726	361
#60	#50	1.5	99.9	0.861	0.867	0.764	12867
#70	#60	11.4	98.4	0.905	0.896	0.763	147465
#140	#70	75.6	87.0	0.906	0.904	0.743	3404876
PAN	#140	11.4	11.4	0.878	0.915	0.716	96556814



Characteristics

Q3 [%]	x [μm]
10.0	102.2
50.0	156.6
90.0	218.2
SPAN3 =	0.741
U3 =	1.664
Mv3(x) =	157.2 μm
Sigma3(x) =	47.8 μm

Mean value SPHT3 = 0.895
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.618
 Mean value SPHT_K3 = 0.655

User