


ENN_15_SV_14_6KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_15_SV_14_6KCRUSH\ENN_15_SV_14_6KCRUSH078.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_15_SV_14_6KCRUSH.afg
 Time: 5/20/2015 , 14:03 , duration 25 min 7 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 52816257 , CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.832	0.865	0.721	31
#50	#40	0.5	100.0	0.834	0.854	0.763	1840
#60	#50	5.4	99.5	0.894	0.890	0.767	39235
#70	#60	14.0	94.1	0.906	0.898	0.753	158111
#140	#70	64.2	80.1	0.919	0.900	0.743	2667205
PAN	#140	15.9	15.9	0.936	0.895	0.717	49949835



Characteristics

Q3 [%]	x [μm]
10.0	82.3
50.0	160.1
90.0	235.4
SPAN3 = 0.956	
U3 = 2.139	
Mv3(x) = 159.9 μm	
Sigma3(x) = 60.0 μm	

Mean value SPHT3 = 0.909
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.731
 Mean value RDNS_C3 = 0.486
 Mean value SPHT_K3 = 0.669

User