


ENN\_15\_SV\_14\_SPHERROUND140

Company:  
 User:  
 Result file: C:\...erXT\CAMDAT\ENN\_15\_SV\_14\_SPHERROUND140\ENN\_15\_SV\_14\_SPHERROUND140029.rdf  
 Task file: C:\CamsizerXT\CAMSYS\ENN\_15\_SV\_14\_SPHERROUND140.afg  
 Time: 4/28/2015 , 13:45 , duration 11 min 10 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 2039287 , CCD-Z = 98225  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.667	0.742	0.712	95
#60	#50	1.6	99.9	0.866	0.869	0.763	4354
#70	#60	14.1	98.3	0.905	0.896	0.761	56510
#140	#70	80.8	84.2	0.900	0.904	0.732	1025776
PAN	#140	3.4	3.4	0.890	0.931	0.681	16281040



Mean value SPHT3 = 0.893  
 Mean value Symm3 = 0.901  
 Mean value b/l3 = 0.719  
 Mean value RDNS\_C3 = 0.629  
 Mean value SPHT\_K3 = 0.636

User