


ENN_16_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_16_SV_14_PRECRUSH\ENN_16_SV_14_PRECRUSH127.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_16_SV_14_PRECRUSH.afg
 Time: 6/12/2015 , 12:19 , duration 7 min 56 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 7351159 , CCD-Z = 96356
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		24.0	100.0	0.778	0.877	0.682	1477
#20	#16	23.1	76.0	0.780	0.879	0.659	3796
#30	#20	17.7	52.9	0.793	0.880	0.659	7855
#40	#30	11.0	35.2	0.808	0.883	0.662	13885
#50	#40	7.7	24.2	0.833	0.884	0.679	28811
#60	#50	3.4	16.5	0.859	0.887	0.699	28449
#70	#60	2.8	13.1	0.878	0.892	0.712	42135
#140	#70	8.9	10.3	0.886	0.900	0.718	456512
PAN	#140	1.4	1.4	0.863	0.912	0.709	23370722



Characteristics

Q3 [%]	x [μm]
10.0	208.8
50.0	809.8
90.0	1438.3
SPAN3 =	1.518
U3 =	4.557
Mv3(x) =	826.5 μm
Sigma3(x) =	462.2 μm

Mean value SPHT3 = 0.797
 Mean value Symm3 = 0.882
 Mean value b/l3 = 0.656
 Mean value RDNS_C3 = 0.294
 Mean value SPHT_K3 = 0.504

User