


ENN_9_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_9_SV_14_PRECRUSH\ENN_9_SV_14_PRECRUSH043.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_9_SV_14_PRECRUSH.afg
 Time: 4/14/2015, 14:29, duration 10 min 14 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4948705, CCD-Z = 9
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		11.3	100.0	0.783	0.886	0.727	774
#20	#16	10.5	88.7	0.791	0.886	0.710	1923
#30	#20	8.6	78.2	0.808	0.884	0.710	4449
#40	#30	7.3	69.6	0.837	0.883	0.726	11121
#50	#40	9.2	62.3	0.867	0.883	0.737	42363
#60	#50	12.3	53.1	0.904	0.897	0.759	126674
#70	#60	18.2	40.8	0.919	0.907	0.753	291880
#140	#70	22.3	22.6	0.918	0.907	0.728	784794
PAN	#140	0.3	0.3	0.924	0.900	0.711	21196



Characteristics

Q3 [%]	x [μm]
10.0	183.4
50.0	281.6
90.0	1226.3
SPAN3 = 3.704	
U3 = 2.095	
Mv3(x) = 517.5 μm	
Sigma3(x) = 427.6 μm	

Mean value SPHT3 = 0.863
 Mean value Symm3 = 0.894
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.360
 Mean value SPHT_K3 = 0.650

User