


ENN_9_SV_14_SPHER_ROUND_140

Company:
 User:
 Result file: C:\...XT\CAMDAT\ENN_9_SV_14_SPHER_ROUND_140\ENN_9_SV_14_SPHER_ROUND_140042.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_9_SV_14_SPHER_ROUND_140.afg
 Time: 4/14/2015, 14:01, duration 8 min 26 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 2140477, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDO
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.690	0.743	0.713	336
#60	#50	2.8	99.9	0.876	0.871	0.765	13083
#70	#60	25.4	97.1	0.922	0.905	0.771	183853
#140	#70	71.0	71.7	0.922	0.907	0.734	1171744
PAN	#140	0.7	0.7	0.896	0.890	0.643	771461



Mean value SPHT3 = 0.913
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.491
 Mean value SPHT_K3 = 0.660

User