


FB_01_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\FB_01_SV_14_PRECRUSH\FB_01_SV_14_PRECRUSH128.rdf
 Task file: C:\CamsizerXT\CAMSYS\FB_01_SV_14_PRECRUSH.afg
 Time: 6/12/2015 , 12:28 , duration 10 min 17 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 7727674 , CCD-Z = 85589
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		7.3	100.0	0.748	0.874	0.716	671
#20	#16	13.3	92.7	0.768	0.873	0.703	3191
#30	#20	18.1	79.4	0.792	0.873	0.704	11731
#40	#30	16.6	61.3	0.814	0.872	0.704	29903
#50	#40	15.0	44.7	0.844	0.876	0.710	76936
#60	#50	8.6	29.7	0.876	0.888	0.725	97280
#70	#60	8.3	21.1	0.896	0.897	0.731	160404
#140	#70	12.3	12.8	0.895	0.901	0.710	553876
PAN	#140	0.5	0.5	0.827	0.901	0.669	25069958



Characteristics

Q3 [%]	x [μm]
10.0	199.5
50.0	476.8
90.0	1094.4
SPAN3 = 1.877	
U3 = 2.932	
Mv3(x) = 567.7 μm	
Sigma3(x) = 357.5 μm	

Mean value SPHT3 = 0.820
 Mean value Symm3 = 0.879
 Mean value b/l3 = 0.695
 Mean value RDNS_C3 = 0.314
 Mean value SPHT_K3 = 0.602

User