


FB_02_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\FB_02_SV_14_PRECRUSH\FB_02_SV_14_PRECRUSH084.rdf
 Task file: C:\CamsizerXT\CAMSYS\FB_02_SV_14_PRECRUSH.afg
 Time: 6/4/2015 , 13:38 , duration 15 min 34 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3770055 , CCD-Z = 46666
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.2	100.0	0.728	0.890	0.710	10
#20	#16	0.3	99.8	0.796	0.881	0.723	62
#30	#20	1.7	99.5	0.851	0.892	0.762	901
#40	#30	5.8	97.8	0.861	0.882	0.751	9083
#50	#40	25.2	92.0	0.891	0.894	0.750	106606
#60	#50	20.9	66.8	0.900	0.899	0.736	172099
#70	#60	17.1	45.9	0.905	0.901	0.727	226469
#140	#70	26.7	28.8	0.896	0.902	0.713	988990
PAN	#140	2.1	2.1	0.829	0.914	0.678	13407673



Characteristics

Q3 [%]	x [μm]
10.0	158.8
50.0	259.1
90.0	404.1
SPAN3 = 0.947	
U3 = 1.777	
Mv3(x) = 277.9 μm	
Sigma3(x) = 124.8 μm	

Mean value SPHT3 = 0.886
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.716
 Mean value RDNS_C3 = 0.505
 Mean value SPHT_K3 = 0.633

User