


FB_03_SV_14_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\FB_03_SV_14_CRUSH6K\FB_03_SV_14_CRUSH6K078.rdf
 Task file: C:\CamsizerXT\CAMSYS\FB_03_SV_14_CRUSH6K.afg
 Time: 6/10/2015, 12:41, duration 30 min 6 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 134991931, CCD-Z = 1473842
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.585	0.861	0.741	9
#20	#16	0.3	99.9	0.657	0.847	0.708	49
#30	#20	0.8	99.6	0.711	0.849	0.710	459
#40	#30	2.3	98.8	0.752	0.849	0.711	3444
#50	#40	5.1	96.5	0.791	0.849	0.714	20889
#60	#50	4.0	91.4	0.830	0.857	0.718	33877
#70	#60	7.1	87.4	0.878	0.880	0.741	103137
#140	#70	67.5	80.3	0.911	0.906	0.748	3416698
PAN	#140	12.8	12.8	0.881	0.909	0.728	181558524



Characteristics

Q3 [%]	x [μm]
10.0	89.7
50.0	160.5
90.0	279.9
SPAN3 =	1.185
U3 =	1.921
Mv3(x) =	180.8 μm
Sigma3(x) =	117.1 μm

Mean value SPHT3 = 0.882
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.536
 Mean value SPHT_K3 = 0.656

User