


FB_03_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\FB_03_SV_14_PRECRUSH\FB_03_SV_14_PRECRUSH088.rdf
 Task file: C:\CamsizerXT\CAMSYS\FB_03_SV_14_PRECRUSH.afg
 Time: 8/10/2015 , 9:26 , duration 6 min 50 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1689551 , CCD-Z = 31710
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		10.1	100.0	0.784	0.881	0.723	757
#20	#16	16.7	89.9	0.796	0.885	0.714	3178
#30	#20	21.6	73.2	0.814	0.883	0.720	11266
#40	#30	19.3	51.6	0.834	0.883	0.723	28098
#50	#40	16.0	32.3	0.856	0.883	0.725	66552
#60	#50	6.9	16.3	0.874	0.885	0.724	61437
#70	#60	4.0	9.4	0.883	0.890	0.710	57165
#140	#70	5.1	5.4	0.892	0.902	0.712	234792
PAN	#140	0.3	0.3	0.845	0.914	0.671	7778172



Characteristics

Q3 [%]	x [μm]
10.0	254.5
50.0	583.5
90.0	1183.4
SPAN3 = 1.592	
U3 = 2.698	
Mv3(x) = 653.9 μm	
Sigma3(x) = 356.3 μm	

Mean value SPHT3 = 0.825
 Mean value Symm3 = 0.884
 Mean value b/l3 = 0.707
 Mean value RDNS_C3 = 0.343
 Mean value SPHT_K3 = 0.630

User