


## GFN\_02\_SV\_14\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\GFN\_02\_SV\_14\_PRECRUSH\GFN\_02\_SV\_14\_PRECRUSH065.rdf  
 Task file: C:\CamsizerXT\CAMSYS\GFN\_02\_SV\_14\_PRECRUSH.afg  
 Time: 5/22/2015, 10:53, duration 11 min 4 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 5764765, CCD-Z = 0  
 Velocity adaption: no  
 Fitting: no

Material:

| ASTM(+) | No(-) | retained [%] | passing [%] | SPHT3 | Symm3 | b/l3  | PD0     |
|---------|-------|--------------|-------------|-------|-------|-------|---------|
| > #16   |       | 11.0         | 100.0       | 0.737 | 0.887 | 0.681 | 170     |
| #20     | #16   | 10.2         | 89.0        | 0.770 | 0.887 | 0.696 | 563     |
| #30     | #20   | 11.2         | 78.8        | 0.781 | 0.887 | 0.700 | 1709    |
| #40     | #30   | 9.8          | 67.6        | 0.804 | 0.885 | 0.715 | 4280    |
| #50     | #40   | 8.5          | 57.8        | 0.826 | 0.881 | 0.724 | 10671   |
| #60     | #50   | 3.9          | 49.3        | 0.842 | 0.879 | 0.729 | 10971   |
| #70     | #60   | 3.5          | 45.4        | 0.853 | 0.877 | 0.731 | 16299   |
| #140    | #70   | 19.3         | 41.9        | 0.890 | 0.879 | 0.737 | 446310  |
| PAN     | #140  | 22.6         | 22.6        | 0.941 | 0.892 | 0.737 | 5273791 |



## Characteristics

| Q3 [%]               | x [μm] |
|----------------------|--------|
| 10.0                 | 77.2   |
| 50.0                 | 309.3  |
| 90.0                 | 1244.4 |
| SPAN3 = 3.773        |        |
| U3 = 5.976           |        |
| Mv3(x) = 502.5 μm    |        |
| Sigma3(x) = 494.2 μm |        |

Mean value SPHT3 = 0.813  
 Mean value Symm3 = 0.883  
 Mean value b/l3 = 0.703  
 Mean value RDNS\_C3 = 0.309  
 Mean value SPHT\_K3 = 0.616

User