


GFS9_Crush6k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\GFS9_Crush6k\GFS9_Crush6k015.rdf
 Task file: C:\CamsizerXT\CAMSYS\GFS9_Crush6k.afg
 Time: 1/26/2015, 14:14, duration 20 min 24 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 99345077, CCD-Z = 600489
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.536	0.678	0.707	16
#40	#30	5.0	100.0	0.882	0.888	0.783	22908
#50	#40	47.1	95.0	0.904	0.904	0.762	463734
#60	#50	22.5	47.9	0.906	0.907	0.735	413332
#70	#60	7.8	25.4	0.896	0.903	0.707	224210
#140	#70	9.4	17.6	0.881	0.897	0.704	964751
PAN	#140	8.2	8.2	0.849	0.901	0.712	236539450



Characteristics

Q3 [%]	x [μm]
10.0	131.0
50.0	303.9
90.0	399.7
SPAN3 = 0.884	
U3 = 2.461	
Mv3(x) = 288.5 μm	
Sigma3(x) = 100.2 μm	

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.571
 Mean value SPHT_K3 = 0.664

User