


GFS_02_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\GFS_02_PRECRUSH\GFS_02_PRECRUSH057.rdf
Task file:	C:\CamsizerXT\CAMSYS\GFS_02_PRECRUSH.afg
Time:	8/12/2015 , 9:27 , duration 6 min 56 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 1687218 , CCD-Z = 26268
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		11.5	100.0	0.784	0.880	0.710	271
#20	#16	13.1	88.5	0.790	0.878	0.692	835
#30	#20	11.8	75.4	0.799	0.876	0.697	2040
#40	#30	9.5	63.6	0.814	0.871	0.701	4745
#50	#40	14.6	54.1	0.870	0.886	0.733	22947
#60	#50	10.9	39.5	0.899	0.901	0.738	34697
#70	#60	8.5	28.6	0.907	0.904	0.734	43463
#140	#70	17.4	20.1	0.898	0.904	0.724	291254
PAN	#140	2.7	2.7	0.842	0.917	0.680	4311319



Mean value SPHT3 = 0.841
Mean value Symm3 = 0.888
Mean value b/l3 = 0.702
Mean value RDNS_C3 = 0.360
Mean value SPHT_K3 = 0.610

User