


GFS_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\GFS_03_PRECRUSH\GFS_03_PRECRUSH229.rdf
 Task file: C:\CamsizerXT\CAMSYS\GFS_03_PRECRUSH.afg
 Time: 7/9/2015 , 10:51 , duration 10 min 27 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 12383901 , CCD-Z = 158972
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		2.0	100.0	0.776	0.895	0.747	105
#20	#16	2.1	98.0	0.782	0.887	0.734	335
#30	#20	2.6	95.9	0.794	0.880	0.734	1181
#40	#30	3.6	93.3	0.816	0.876	0.745	4957
#50	#40	7.5	89.7	0.844	0.872	0.747	29042
#60	#50	7.2	82.2	0.869	0.876	0.747	57676
#70	#60	10.6	75.0	0.898	0.891	0.752	141938
#140	#70	57.7	64.4	0.916	0.912	0.747	2544844
PAN	#140	6.7	6.7	0.895	0.930	0.739	23203665



Characteristics

Q3 [%]	x [μm]
10.0	116.5
50.0	183.8
90.0	436.2
SPAN3 =	1.740
U3 =	1.733
Mv3(x) =	256.7 μm
Sigma3(x) =	247.3 μm

Mean value SPHT3 = 0.886
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.520
 Mean value SPHT_K3 = 0.676

User