


GFS_05_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\GFS_05_PRECRUSH\GFS_05_PRECRUSH215.rdf
 Task file: C:\CamsizerXT\CAMSYS\GFS_05_PRECRUSH.afg
 Time: 7/8/2015 , 14:53 , duration 9 min 50 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 11390535 , CCD-Z = 152440
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.1	100.0	0.765	0.864	0.733	21
#30	#20	0.3	99.9	0.807	0.876	0.759	161
#40	#30	2.6	99.6	0.826	0.866	0.755	4222
#50	#40	13.0	97.0	0.858	0.871	0.746	54919
#60	#50	20.0	84.0	0.896	0.891	0.750	167684
#70	#60	25.7	64.0	0.911	0.902	0.740	339344
#140	#70	36.5	38.3	0.907	0.908	0.715	1155197
PAN	#140	1.8	1.8	0.862	0.917	0.700	28948291



Characteristics

Q3 [%]	x [μm]
10.0	158.7
50.0	228.4
90.0	332.8
SPAN3 =	0.762
U3 =	1.534
Mv3(x) =	240.0 μm
Sigma3(x) =	81.7 μm

Mean value SPHT3 = 0.889
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.718
 Mean value RDNS_C3 = 0.519
 Mean value SPHT_K3 = 0.638

User