


GFS_06_CRUSH5K

Company:
User:
Result file: C:\CamsizerXT\CAMDAT\GFS_06_CRUSH5K\GFS_06_CRUSH5K059.rdf
Task file: C:\CamsizerXT\CAMSYS\GFS_06_CRUSH5K.afg
Time: 8/12/2015, 11:45, duration 23 min 24 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
No. of particles: CCD-B = 78139591, CCD-Z = 684052
Velocity adaption: no
Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.773	0.823	0.757	3
#40	#30	0.7	100.0	0.854	0.871	0.781	2087
#50	#40	16.2	99.3	0.893	0.893	0.770	119087
#60	#50	29.4	83.1	0.911	0.904	0.765	401581
#70	#60	25.5	53.7	0.913	0.908	0.742	519258
#140	#70	20.7	28.2	0.893	0.901	0.708	1157614
PAN	#140	7.5	7.5	0.855	0.901	0.709	99389095



Characteristics

Q3 [%]	x [μm]
10.0	130.5
50.0	245.1
90.0	323.2
SPAN3 = 0.786	
U3 = 1.980	
Mv3(x) = 237.7 μm	
Sigma3(x) = 76.8 μm	

Mean value SPHT3 = 0.895
Mean value Symm3 = 0.901
Mean value b/l3 = 0.730
Mean value RDNS_C3 = 0.545
Mean value SPHT_K3 = 0.666

User