


GFS_06_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\GFS_06_SV_14_PRECRUSH\GFS_06_SV_14_PRECRUSH175.rdf
 Task file: C:\CamsizerXT\CAMSYS\GFS_06_SV_14_PRECRUSH.afg
 Time: 6/24/2015 , 16:12 , duration 11 min 53 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 11493478 , CCD-Z = 141348
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.8	100.0	0.750	0.880	0.740	59
#20	#16	4.4	98.2	0.749	0.875	0.722	327
#30	#20	5.2	93.8	0.778	0.866	0.725	1095
#40	#30	7.8	88.6	0.805	0.861	0.725	4584
#50	#40	13.8	80.8	0.861	0.877	0.736	24248
#60	#50	15.1	67.0	0.898	0.897	0.746	54693
#70	#60	18.7	51.9	0.913	0.906	0.744	109696
#140	#70	29.3	33.2	0.906	0.907	0.717	427933
PAN	#140	3.9	3.9	0.868	0.910	0.709	26181468



Characteristics

Q3 [%]	x [μm]
10.0	153.0
50.0	245.4
90.0	651.1
SPAN3 = 2.030	
U3 = 1.783	
Mv3(x) = 329.9 μm	
Sigma3(x) = 244.9 μm	

Mean value SPHT3 = 0.868
 Mean value Symm3 = 0.892
 Mean value b/l3 = 0.716
 Mean value RDNS_C3 = 0.409
 Mean value SPHT_K3 = 0.640

User