


GFS_10_SV_14_CRUSH7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\GFS_10_SV_14_CRUSH7K\GFS_10_SV_14_CRUSH7K050.rdf
 Task file: C:\CamsizerXT\CAMSYS\GFS_10_SV_14_CRUSH7K.afg
 Time: 7/6/2015 , 10:57 , duration 28 min 30 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 163519344 , CCD-Z = 1386257
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.682	0.828	0.712	4
#50	#40	0.1	100.0	0.714	0.771	0.722	910
#60	#50	1.8	99.9	0.874	0.873	0.772	32383
#70	#60	17.1	98.1	0.916	0.901	0.774	455290
#140	#70	69.1	81.0	0.911	0.905	0.741	5127125
PAN	#140	11.9	11.9	0.872	0.908	0.709	230113632



Characteristics

Q3 [%]	x [μm]
10.0	97.0
50.0	176.1
90.0	225.2
SPAN3 = 0.728	
U3 = 1.937	
Mv3(x) = 167.5 μm	
Sigma3(x) = 51.6 μm	

Mean value SPHT3 = 0.900
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.605
 Mean value SPHT_K3 = 0.658

User