


GFS_10_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\GFS_10_SV_14_PRECRUSH\GFS_10_SV_14_PRECRUSH209.rdf
 Task file: C:\CamsizerXT\CAMSYS\GFS_10_SV_14_PRECRUSH.afg
 Time: 6/29/2015 , 16:22 , duration 8 min 56 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1866105 , CCD-Z = 26231
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		20.3	100.0	0.740	0.875	0.695	1087
#20	#16	14.0	79.7	0.743	0.871	0.675	2196
#30	#20	13.5	65.7	0.770	0.868	0.691	5824
#40	#30	9.6	52.2	0.789	0.861	0.693	11869
#50	#40	12.2	42.6	0.841	0.868	0.720	48773
#60	#50	14.8	30.4	0.893	0.892	0.745	126221
#70	#60	11.7	15.6	0.906	0.903	0.723	144786
#140	#70	3.6	3.9	0.881	0.902	0.650	79724
PAN	#140	0.3	0.3	0.818	0.904	0.667	6593353



Characteristics

Q3 [%]	x [μm]
10.0	234.8
50.0	557.9
90.0	1453.7
SPAN3 =	2.185
U3 =	3.162
Mv3(x) =	702.3 μm
Sigma3(x) =	471.6 μm

Mean value SPHT3 = 0.803
 Mean value Symm3 = 0.877
 Mean value b/l3 = 0.690
 Mean value RDNS_C3 = 0.296
 Mean value SPHT_K3 = 0.591

User