


GFS_15_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\GFS_15_PRECRUSH\GFS_15_PRECRUSH231.rdf
 Task file: C:\CamsizerXT\CAMSYS\GFS_15_PRECRUSH.afg
 Time: 7/9/2015 , 11:12 , duration 10 min 32 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 14282764 , CCD-Z = 294904
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		3.0	100.0	0.777	0.889	0.739	168
#20	#16	7.1	97.0	0.794	0.894	0.722	915
#30	#20	6.7	89.9	0.813	0.892	0.738	2440
#40	#30	5.9	83.2	0.826	0.885	0.743	6383
#50	#40	6.6	77.3	0.845	0.880	0.745	20784
#60	#50	4.8	70.7	0.863	0.878	0.748	32250
#70	#60	5.9	65.9	0.883	0.885	0.750	66300
#140	#70	46.6	60.0	0.911	0.907	0.749	2405203
PAN	#140	13.4	13.4	0.913	0.935	0.745	37671906



Characteristics

Q3 [%]	x [μm]
10.0	99.1
50.0	172.1
90.0	853.2
SPAN3 = 4.383	
U3 = 2.140	
Mv3(x) = 322.4 μm	
Sigma3(x) = 330.6 μm	

Mean value SPHT3 = 0.875
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.732
 Mean value RDNS_C3 = 0.521
 Mean value SPHT_K3 = 0.674

User