


GFS\_22\_SV\_14\_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\GFS_22_SV_14_PRECRUSH\GFS_22_SV_14_PRECRUSH103.rdf
Task file:	C:\CamsizerXT\CAMSYS\GFS_22_SV_14_PRECRUSH.afg
Time:	6/9/2015 , 9:20 , duration 13 min 44 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 2819493 , CCD-Z = 42194
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.2	100.0	0.589	0.885	0.624	3
#20	#16	0.5	99.8	0.811	0.880	0.707	29
#30	#20	1.2	99.3	0.855	0.886	0.737	307
#40	#30	8.8	98.1	0.880	0.891	0.743	5656
#50	#40	25.3	89.3	0.889	0.896	0.726	41211
#60	#50	15.4	64.0	0.894	0.898	0.716	50885
#70	#60	12.9	48.6	0.900	0.901	0.714	72008
#140	#70	29.8	35.7	0.891	0.902	0.704	555253
PAN	#140	5.9	5.9	0.852	0.921	0.687	7274060



Mean value SPHT3 = 0.879
Mean value Symm3 = 0.899
Mean value b/l3 = 0.696
Mean value RDNS_C3 = 0.546
Mean value SPHT_K3 = 0.582

User