


HL_02_SV_14_CRUSH5K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\HL_02_SV_14_CRUSH5K\HL_02_SV_14_CRUSH5K080.rdf
Task file:	C:\CamsizerXT\CAMSYS\HL_02_SV_14_CRUSH5K.afg
Time:	6/10/2015 , 15:36 , duration 22 min 43 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 31684969 , CCD-Z = 333854
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.674	0.740	0.726	125
#60	#50	1.1	100.0	0.876	0.872	0.775	6972
#70	#60	11.1	98.9	0.918	0.902	0.775	115078
#140	#70	79.9	87.8	0.912	0.906	0.743	2525561
PAN	#140	7.9	7.9	0.856	0.902	0.677	52916398



Mean value SPHT3 = 0.902
Mean value Symm3 = 0.903
Mean value b/l3 = 0.728
Mean value RDNS_C3 = 0.563
Mean value SPHT_K3 = 0.657

User