


HL_02_SV_14_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\HL_02_SV_14_CRUSH6K\HL_02_SV_14_CRUSH6K079.rdf
 Task file: C:\CamsizerXT\CAMSYS\HL_02_SV_14_CRUSH6K.afg
 Time: 6/10/2015, 14:04, duration 26 min 38 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 45759115, CCD-Z = 659677
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.648	0.772	0.548	4
#50	#40	0.0	100.0	0.724	0.772	0.730	115
#60	#50	1.0	100.0	0.883	0.878	0.779	6618
#70	#60	10.9	99.0	0.920	0.903	0.778	113620
#140	#70	77.9	88.1	0.916	0.909	0.747	2546798
PAN	#140	10.2	10.2	0.883	0.915	0.709	76048442



Mean value SPHT3 = 0.907
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.732
 Mean value RDNS_C3 = 0.637
 Mean value SPHT_K3 = 0.665

User