


HL_03_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\HL_03_SV_14_CRUSH_6K\HL_03_SV_14_CRUSH_6K081.rdf
 Task file: C:\CamsizerXT\CAMSYS\HL_03_SV_14_CRUSH_6K.afg
 Time: 6/4/2015 , 12:20 , duration 26 min 54 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 29087230 , CCD-Z = 327572
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.761	0.842	0.773	5
#50	#40	0.2	100.0	0.741	0.783	0.729	684
#60	#50	2.2	99.8	0.881	0.875	0.768	17831
#70	#60	20.9	97.6	0.925	0.907	0.776	259994
#140	#70	72.2	76.7	0.919	0.911	0.739	2055748
PAN	#140	4.5	4.5	0.840	0.901	0.671	92397387



Characteristics

Q3 [%]	x [μm]
10.0	131.8
50.0	188.4
90.0	228.3
SPAN3 = 0.512	
U3 = 1.495	
Mv3(x) = 183.1 μm	
Sigma3(x) = 41.8 μm	

Mean value SPHT3 = 0.910
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.731
 Mean value RDNS_C3 = 0.552
 Mean value SPHT_K3 = 0.662

User