


HL_03_SV_14_CRUSH_7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\HL_03_SV_14_CRUSH_7K\HL_03_SV_14_CRUSH_7K105.rdf
 Task file: C:\CamsizerXT\CAMSYS\HL_03_SV_14_CRUSH_7K.afg
 Time: 6/9/2015, 12:22, duration 33 min 19 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 40112522, CCD-Z = 389475
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.696	0.854	0.746	1
#40	#30	0.0	100.0	0.826	0.871	0.725	13
#50	#40	0.1	100.0	0.788	0.834	0.728	223
#60	#50	1.1	99.9	0.890	0.881	0.783	5075
#70	#60	15.3	98.8	0.934	0.912	0.790	112772
#140	#70	72.9	83.5	0.924	0.912	0.751	1332536
PAN	#140	10.6	10.6	0.847	0.894	0.671	163790167



Characteristics

Q3 [%]	x [μm]
10.0	102.6
50.0	178.4
90.0	221.1
SPAN3 = 0.664	
U3 = 1.834	
Mv3(x) = 169.2 μm	
Sigma3(x) = 49.2 μm	

Mean value SPHT3 = 0.913
 Mean value Symm3 = 0.908
 Mean value b/l3 = 0.737
 Mean value RDNS_C3 = 0.481
 Mean value SPHT_K3 = 0.679

User