


HL_03_SV_14_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\HL_03_SV_14_PRECRUSH\HL_03_SV_14_PRECRUSH054.rdf
Task file:	C:\CamsizerXT\CAMSYS\HL_03_SV_14_PRECRUSH.afg
Time:	5/22/2015 , 14:42 , duration 8 min 30 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 4393492 , CCD-Z = 66816
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		10.0	100.0	0.719	0.879	0.670	534
#20	#16	7.1	90.0	0.744	0.873	0.699	1546
#30	#20	8.0	82.9	0.774	0.872	0.705	4663
#40	#30	8.0	74.9	0.807	0.868	0.718	13715
#50	#40	11.5	66.9	0.854	0.874	0.732	58883
#60	#50	11.7	55.4	0.898	0.894	0.748	125807
#70	#60	16.3	43.7	0.920	0.908	0.753	293807
#140	#70	26.9	27.4	0.917	0.912	0.730	1092226
PAN	#140	0.5	0.5	0.873	0.911	0.686	13367342



Mean value SPHT3 = 0.850
Mean value Symm3 = 0.891
Mean value b/l3 = 0.711
Mean value RDNS_C3 = 0.347
Mean value SPHT_K3 = 0.631

User