


HL_05_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\HL_05_PRECRUSH\HL_05_PRECRUSH072.rdf
Task file:	C:\CamsizerXT\CAMSYS\HL_05_PRECRUSH.afg
Time:	3/10/2015 , 14:56 , duration 5 min 27 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 4138349 , CCD-Z = 60
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		9.5	100.0	0.812	0.883	0.720	838
#20	#16	11.9	90.5	0.830	0.885	0.719	2974
#30	#20	16.9	78.6	0.854	0.890	0.728	11741
#40	#30	20.3	61.7	0.871	0.893	0.726	39321
#50	#40	19.5	41.4	0.885	0.897	0.723	104055
#60	#50	7.0	21.9	0.888	0.898	0.712	79120
#70	#60	3.8	14.9	0.889	0.898	0.702	71718
#140	#70	4.2	11.1	0.890	0.896	0.691	202087
PAN	#140	6.9	6.9	0.877	0.888	0.657	41188



Mean value SPHT3 = 0.856
Mean value Symm3 = 0.891
Mean value b/l3 = 0.705
Mean value RDNS_C3 = 0.443
Mean value SPHT_K3 = 0.616

User