


HL_4_SANDR140

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\HL_4_SANDR140\HL_4_SANDR140061.rdf
Task file:	C:\CamsizerXT\CAMSYS\HL_4_SANDR140.afg
Time:	3/9/2015 , 16:31 , duration 4 min 36 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 2439592 , CCD-Z = 1695
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.839	0.852	0.664	2
#40	#30	0.0	100.0	0.919	0.918	0.855	3
#50	#40	0.1	100.0	0.658	0.717	0.715	293
#60	#50	2.2	99.9	0.868	0.863	0.763	9595
#70	#60	19.8	97.7	0.920	0.902	0.772	135486
#140	#70	77.3	77.9	0.914	0.908	0.736	1203724
PAN	#140	0.6	0.6	0.871	0.628	0.636	2668101



Mean value SPHT3 = 0.907
Mean value Symm3 = 0.902
Mean value b/l3 = 0.730
Mean value RDNS_C3 = 0.424
Mean value SPHT_K3 = 0.663

User