


HL_5_6KCRUSH_02

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\HL_5_6KCRUSH_02\HL_5_6KCRUSH_02047.rdf
 Task file: C:\CamsizerXT\CAMSYS\HL_5_6KCRUSH_02.afg
 Time: 8/11/2015 , 14:06 , duration 19 min 27 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 82404617 , CCD-Z = 804054
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.680	0.813	0.739	12
#30	#20	6.0	100.0	0.875	0.893	0.777	6139
#40	#30	36.5	94.0	0.885	0.900	0.749	76619
#50	#40	32.3	57.5	0.888	0.899	0.735	175300
#60	#50	7.2	25.2	0.875	0.893	0.704	82994
#70	#60	3.7	18.0	0.871	0.888	0.697	72493
#140	#70	8.1	14.3	0.858	0.885	0.676	549692
PAN	#140	6.2	6.2	0.835	0.893	0.669	129915423



Characteristics

Q3 [%]	x [μm]
10.0	159.2
50.0	396.7
90.0	571.5
SPAN3 =	1.039
U3 =	2.731
Mv3(x) =	385.1 μm
Sigma3(x) =	151.5 μm

Mean value SPHT3 = 0.873
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.715
 Mean value RDNS_C3 = 0.515
 Mean value SPHT_K3 = 0.635

User