


LIMA_02_SV_14_CRUSH_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_02_SV_14_CRUSH_5K\LIMA_02_SV_14_CRUSH_5K067.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_02_SV_14_CRUSH_5K.afg
 Time: 5/19/2015, 13:51, duration 18 min 14 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 10095393, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	1.0	100.0	0.891	0.889	0.798	557
#50	#40	24.4	99.0	0.913	0.904	0.779	29483
#60	#50	28.2	74.6	0.919	0.908	0.764	63693
#70	#60	19.7	46.4	0.918	0.909	0.742	68692
#140	#70	19.6	26.7	0.912	0.901	0.725	216626
PAN	#140	7.1	7.1	0.928	0.891	0.702	9716343



Characteristics

Q3 [%]	x [μm]
10.0	132.2
50.0	255.7
90.0	347.4
SPAN3 = 0.841	
U3 = 2.057	
Mv3(x) = 247.9 μm	
Sigma3(x) = 84.5 μm	

Mean value SPHT3 = 0.911
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.742
 Mean value RDNS_C3 = 0.649
 Mean value SPHT_K3 = 0.693

User