


LIMA_02_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_02_SV_14_CRUSH_6K\LIMA_02_SV_14_CRUSH_6K058.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_02_SV_14_CRUSH_6K.afg
 Time: 5/19/2015, 10:43, duration 18 min 4 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 53321737, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.806	0.909	0.643	1
#40	#30	0.9	100.0	0.894	0.893	0.803	1437
#50	#40	22.7	99.1	0.915	0.906	0.781	81508
#60	#50	25.6	76.4	0.919	0.909	0.764	169588
#70	#60	18.1	50.8	0.919	0.909	0.745	188545
#140	#70	21.3	32.7	0.914	0.901	0.730	730377
PAN	#140	11.4	11.4	0.930	0.892	0.703	52150280



Characteristics

Q3 [%]	x [μm]
10.0	90.7
50.0	248.5
90.0	343.3
SPAN3 =	1.016
U3 =	2.939
Mv3(x) =	235.3 μm
Sigma3(x) =	93.2 μm

Mean value SPHT3 = 0.912
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.744
 Mean value RDNS_C3 = 0.654
 Mean value SPHT_K3 = 0.697

User