


LIMA_03_SV_14_CRUSH_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_03_SV_14_CRUSH_5K\LIMA_03_SV_14_CRUSH_5K063.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_03_SV_14_CRUSH_5K.afg
 Time: 5/19/2015, 11:38, duration 19 min 31 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 9227234, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.723	0.919	0.512	1
#50	#40	0.1	100.0	0.712	0.767	0.721	97
#60	#50	1.9	99.9	0.892	0.880	0.781	4512
#70	#60	17.6	98.0	0.923	0.903	0.777	65460
#140	#70	72.1	80.4	0.923	0.904	0.743	680736
PAN	#140	8.3	8.3	0.929	0.891	0.705	8476429



Characteristics

Q3 [%]	x [μm]
10.0	115.7
50.0	180.3
90.0	225.9
SPAN3 =	0.611
U3 =	1.644
Mv3(x) =	173.6 μm
Sigma3(x) =	47.8 μm

Mean value SPHT3 = 0.917
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.736
 Mean value RDNS_C3 = 0.489
 Mean value SPHT_K3 = 0.678

User