


LIMA_03_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_03_SV_14_CRUSH_6K\LIMA_03_SV_14_CRUSH_6K055.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_03_SV_14_CRUSH_6K.afg
 Time: 5/19/2015, 10:11, duration 25 min 28 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 33974226, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.833	0.902	0.790	4
#40	#30	0.0	100.0	0.866	0.902	0.710	5
#50	#40	0.1	100.0	0.725	0.769	0.728	115
#60	#50	1.5	99.9	0.896	0.883	0.783	8261
#70	#60	14.9	98.4	0.925	0.904	0.780	126094
#140	#70	70.5	83.5	0.925	0.904	0.748	1603797
PAN	#140	13.0	13.0	0.931	0.891	0.707	32235950



Characteristics

Q3 [%]	x [μm]
10.0	84.2
50.0	173.4
90.0	222.4
SPAN3 =	0.797
U3 =	2.190
Mv3(x) =	164.6 μm
Sigma3(x) =	54.0 μm

Mean value SPHT3 = 0.919
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.740
 Mean value RDNS_C3 = 0.475
 Mean value SPHT_K3 = 0.688

User