


LIMA_04_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_04_SV_14_CRUSH_6K\LIMA_04_SV_14_CRUSH_6K049.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_04_SV_14_CRUSH_6K.afg
 Time: 5/18/2015, 11:50, duration 29 min 12 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 78881167, CCD-Z = 746739
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.648	0.736	0.716	180
#60	#50	0.7	100.0	0.872	0.867	0.782	9863
#70	#60	8.5	99.3	0.918	0.899	0.786	191548
#140	#70	82.9	90.8	0.916	0.907	0.750	5469537
PAN	#140	7.9	7.9	0.856	0.902	0.687	177004324



Characteristics

Q3 [%]	x [μm]
10.0	113.1
50.0	164.0
90.0	210.4
SPAN3 = 0.593	
U3 = 1.531	
Mv3(x) = 160.8 μm	
Sigma3(x) = 42.0 μm	

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.735
 Mean value RDNS_C3 = 0.587
 Mean value SPHT_K3 = 0.673

User