


LIMA_04_SV_14_CRUSH_7k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_04_SV_14_CRUSH_7k\LIMA_04_SV_14_CRUSH_7k052.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_04_SV_14_CRUSH_7k.afg
 Time: 5/18/2015, 14:01, duration 29 min 0 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 45748054, CCD-Z = 101767
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.792	0.827	0.699	1
#50	#40	0.0	100.0	0.707	0.757	0.748	109
#60	#50	0.8	100.0	0.883	0.873	0.785	7339
#70	#60	9.3	99.2	0.922	0.901	0.785	136931
#140	#70	81.1	89.9	0.913	0.906	0.748	3412068
PAN	#140	8.8	8.8	0.821	0.883	0.660	112635934



Characteristics

Q3 [%]	x [μm]
10.0	111.0
50.0	165.2
90.0	212.2
SPAN3 =	0.613
U3 =	1.572
Mv3(x) =	161.2 μm
Sigma3(x) =	43.7 μm

Mean value SPHT3 = 0.900
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.732
 Mean value RDNS_C3 = 0.393
 Mean value SPHT_K3 = 0.670

User