


LIMA_04_SV_14_CRUSH_8K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_04_SV_14_CRUSH_8K\LIMA_04_SV_14_CRUSH_8K069.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_04_SV_14_CRUSH_8K.afg
 Time: 5/19/2015, 14:22, duration 24 min 37 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 9386287, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.720	0.781	0.703	25
#60	#50	0.8	100.0	0.878	0.872	0.783	1251
#70	#60	8.8	99.2	0.920	0.899	0.784	21796
#140	#70	77.9	90.4	0.927	0.904	0.751	578144
PAN	#140	12.5	12.5	0.930	0.891	0.705	8785071



Characteristics

Q3 [%]	x [μm]
10.0	91.8
50.0	161.5
90.0	211.2
SPAN3 = 0.739	
U3 = 1.870	
Mv3(x) = 156.0 μm	
Sigma3(x) = 48.6 μm	

Mean value SPHT3 = 0.920
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.741
 Mean value RDNS_C3 = 0.494
 Mean value SPHT_K3 = 0.690

User