


LIMA_04_SV_14_SPHERROUND140

Company:	
User:	
Result file:	C:\...rXT\CAMDAT\LIMA_04_SV_14_SPHERROUND140\LIMA_04_SV_14_SPHERROUND140031.rdf
Task file:	C:\CamsizerXT\CAMSYS\LIMA_04_SV_14_SPHERROUND140.afg
Time:	4/28/2015 , 14:52 , duration 12 min 28 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 1647464 , CCD-Z = 43437
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.950	0.919	0.783	1
#50	#40	0.0	100.0	0.645	0.727	0.734	64
#60	#50	1.1	100.0	0.851	0.853	0.764	3042
#70	#60	11.1	98.9	0.906	0.891	0.771	48629
#140	#70	86.6	87.8	0.910	0.906	0.740	1050218
PAN	#140	1.2	1.2	0.884	0.931	0.666	4365288



Mean value SPHT3 = 0.902
Mean value Symm3 = 0.902
Mean value b/l3 = 0.728
Mean value RDNS_C3 = 0.655
Mean value SPHT_K3 = 0.657

User