


LIMA_05_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_05_SV_14_CRUSH_6K\LIMA_05_SV_14_CRUSH_6K043.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_05_SV_14_CRUSH_6K.afg
 Time: 5/15/2015 , 13:10 , duration 26 min 3 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 54131892 , CCD-Z = 740263
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.720	0.777	0.730	306
#60	#50	1.2	99.9	0.878	0.873	0.775	11326
#70	#60	12.0	98.7	0.920	0.902	0.778	171169
#140	#70	78.1	86.7	0.916	0.907	0.747	3279275
PAN	#140	8.6	8.6	0.876	0.911	0.704	106680287



Characteristics

Q3 [%]	x [μm]
10.0	110.8
50.0	168.1
90.0	217.9
SPAN3 =	0.638
U3 =	1.614
Mv3(x) =	164.5 μm
Sigma3(x) =	44.9 μm

Mean value SPHT3 = 0.907
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.619
 Mean value SPHT_K3 = 0.668

User