


LIMA_05_SV_14_CRUSH_7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_05_SV_14_CRUSH_7K\LIMA_05_SV_14_CRUSH_7K044.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_05_SV_14_CRUSH_7K.afg
 Time: 5/15/2015, 14:13, duration 25 min 20 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 48181320, CCD-Z = 682595
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.559	0.762	0.663	1
#50	#40	0.1	100.0	0.710	0.772	0.719	277
#60	#50	1.1	99.9	0.871	0.870	0.772	6201
#70	#60	11.3	98.8	0.917	0.901	0.777	94263
#140	#70	76.3	87.5	0.915	0.906	0.747	1895861
PAN	#140	11.2	11.2	0.872	0.907	0.700	103657616



Characteristics

Q3 [%]	x [μm]
10.0	100.9
50.0	165.2
90.0	216.7
SPAN3 =	0.701
U3 =	1.747
Mv3(x) =	160.7 μm
Sigma3(x) =	47.9 μm

Mean value SPHT3 = 0.904
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.732
 Mean value RDNS_C3 = 0.604
 Mean value SPHT_K3 = 0.666

User