


LIMA_05_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_05_SV_14_PRECRUSH\LIMA_05_SV_14_PRECRUSH050.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_05_SV_14_PRECRUSH.afg
 Time: 5/13/2015 , 15:13 , duration 9 min 45 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4914940 , CCD-Z = 78969
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		18.9	100.0	0.712	0.876	0.675	843
#20	#16	9.2	81.1	0.748	0.876	0.689	1817
#30	#20	8.5	71.9	0.770	0.872	0.694	4609
#40	#30	7.9	63.4	0.802	0.869	0.709	12763
#50	#40	12.3	55.5	0.865	0.883	0.737	60087
#60	#50	9.4	43.2	0.894	0.893	0.741	94449
#70	#60	9.5	33.8	0.906	0.899	0.740	160115
#140	#70	23.1	24.3	0.906	0.905	0.731	1152786
PAN	#140	1.2	1.2	0.871	0.918	0.696	12355324



Characteristics

Q3 [%]	x [μm]
10.0	161.0
50.0	353.8
90.0	1646.6
SPAN3 =	4.199
U3 =	3.199
Mv3(x) =	671.1 μm
Sigma3(x) =	654.7 μm

Mean value SPHT3 = 0.823
 Mean value Symm3 = 0.886
 Mean value b/l3 = 0.700
 Mean value RDNS_C3 = 0.336
 Mean value SPHT_K3 = 0.608

User