


LIMA_06_SV_14_CRUSH_5k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_06_SV_14_CRUSH_5k\LIMA_06_SV_14_CRUSH_5k054.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_06_SV_14_CRUSH_5k.afg
 Time: 5/18/2015, 15:25, duration 15 min 54 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 15750706, CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PD0
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.5	100.0	0.840	0.861	0.780	1502
#50	#40	21.5	99.5	0.916	0.903	0.786	177942
#60	#50	35.2	78.0	0.923	0.909	0.766	500990
#70	#60	23.5	42.8	0.920	0.909	0.741	510558
#140	#70	16.6	19.3	0.909	0.901	0.713	969246
PAN	#140	2.7	2.7	0.916	0.886	0.689	13590468



Characteristics

Q3 [%]	x [μm]
10.0	179.0
50.0	259.2
90.0	328.9
SPAN3 = 0.578	
U3 = 1.521	
Mv3(x) = 255.9 μm	
Sigma3(x) = 63.8 μm	

Mean value SPHT3 = 0.913
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.743
 Mean value RDNS_C3 = 0.666
 Mean value SPHT_K3 = 0.693

User