


LIMA_06_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\LIMA_06_SV_14_CRUSH_6K\LIMA_06_SV_14_CRUSH_6K051.rdf
 Task file: C:\CamsizerXT\CAMSYS\LIMA_06_SV_14_CRUSH_6K.afg
 Time: 5/18/2015, 12:58, duration 26 min 18 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 73814947, CCD-Z = 337552
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.719	0.769	0.858	1
#40	#30	0.4	100.0	0.842	0.864	0.778	1233
#50	#40	19.9	99.6	0.915	0.904	0.787	148300
#60	#50	33.3	79.7	0.921	0.909	0.767	429521
#70	#60	22.6	46.4	0.918	0.909	0.743	439157
#140	#70	18.5	23.8	0.897	0.900	0.714	1027050
PAN	#140	5.3	5.3	0.820	0.881	0.649	154569739



Characteristics

Q3 [%]	x [μm]
10.0	152.4
50.0	254.9
90.0	325.7
SPAN3 =	0.680
U3 =	1.762
Mv3(x) =	246.8 μm
Sigma3(x) =	72.0 μm

Mean value SPHT3 = 0.904
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.737
 Mean value RDNS_C3 = 0.599
 Mean value SPHT_K3 = 0.683

User