


LIMA_06_SV_14_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\LIMA_06_SV_14_PRECRUSH\LIMA_06_SV_14_PRECRUSH046.rdf
Task file:	C:\CamsizerXT\CAMSYS\LIMA_06_SV_14_PRECRUSH.afg
Time:	5/14/2015 , 13:57 , duration 8 min 54 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 4088528 , CCD-Z = 76135
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		15.3	100.0	0.725	0.878	0.684	797
#20	#16	8.3	84.7	0.751	0.875	0.687	1726
#30	#20	7.5	76.4	0.770	0.869	0.694	4379
#40	#30	6.9	68.9	0.801	0.864	0.707	11677
#50	#40	14.2	62.0	0.881	0.888	0.751	80517
#60	#50	16.4	47.8	0.912	0.904	0.753	178096
#70	#60	14.0	31.4	0.917	0.907	0.743	243963
#140	#70	17.1	17.4	0.910	0.907	0.722	686349
PAN	#140	0.3	0.3	0.861	0.912	0.678	11469549



Mean value SPHT3 = 0.842
Mean value Symm3 = 0.890
Mean value b/l3 = 0.709
Mean value RDNS_C3 = 0.378
Mean value SPHT_K3 = 0.626

User