


LIMA\_07\_SV\_14\_CRUSH\_5k

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\LIMA\_07\_SV\_14\_CRUSH\_5k\LIMA\_07\_SV\_14\_CRUSH\_5k072.rdf  
 Task file: C:\CamsizerXT\CAMSYS\LIMA\_07\_SV\_14\_CRUSH\_5k.afg  
 Time: 5/19/2015 , 14:53 , duration 21 min 55 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 18656102 , CCD-Z = 0  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDO
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.836	0.894	0.697	2
#40	#30	0.0	100.0	0.815	0.929	0.738	2
#50	#40	0.0	100.0	0.711	0.784	0.717	31
#60	#50	0.6	100.0	0.884	0.875	0.785	1843
#70	#60	7.7	99.4	0.924	0.904	0.786	37092
#140	#70	78.3	91.7	0.931	0.906	0.757	1228579
PAN	#140	13.4	13.4	0.935	0.894	0.714	17388553



Mean value SPHT3 = 0.925  
 Mean value Symm3 = 0.904  
 Mean value b/l3 = 0.747  
 Mean value RDNS\_C3 = 0.513  
 Mean value SPHT\_K3 = 0.706

User